

Bolo Phase I Drill Assays

DH	Gold Values			Silver Values			T.D. (ft)
	Interval (Ftg)	Thickness (ft)	Au (g/t)	Interval (Ft)	Thickness (ft)	Ag (g/t)	
BL-1	20-45	25	0.21		None		425
BL-2		None			None		500
BL-3	25-110	85	0.431	40-45	5	11.3	
	130-135	5	0.106	95-110	15	34.5	360
				125-140	15	26.6	
				240-255	15	21.9	
BL-4	200-260	60	1.086	255-260	5	12.7	
	275-280	5	0.112				285
BL-5	175-180	5	0.279				
	230-245	15	0.141	240-255	15	48.8	485
				345-365	20	13.8	
BL-6		None			None		575
BL-7	0-5	5	0.104		None		605
BL-8	5-10	5	0.117				
	125-135	10	0.126		None		500
BL-9	375-380	5	0.371		None		665
BL-10	125-155	30	0.297		None		605
BL-11	35-40	5	0.104		None		
	70-90	20	0.231				
	345-365	20	0.332				
	390-445	55	0.611				
	incl. 395-410	15	1.681				500
BL-12	220-245	25	0.214	230-235	5	11.7	385
BL-13	0-15	15	0.147				330
	210-215	5	0.108				
	290-320	30	0.135	290-295	5	14.0	
BL-14	430-450	20	0.14		None		500
BL-15	295-300	5	0.222		None		705
BL-16	400-405	5	0.245	405-410	5	15.5	600
BL-17		None		320-325	5	10.1	605
BL-18		None			None		655
BL-19	145-150	5	0.14		None		605
						TOTAL FTG:	9890